Copenhagen

Design:
Norm Architects

Caratteristiche tecniche Copenhagen

Technical specifications / caractéristiques techniques / technische eigenschaften / технические характеристики

Gres porcellanato smaltato, rettificato - Porcelain gres glazed, rectified - Grès porcelainé émaillé, rectifié - Glasiertes Feinsteinzeug, entgratet - керамогранит Эмалированная, ректифицированны

ISO 13006 - UNI EN 14411 Annex G Bla GL

Spessore - Thickness **9 mm**	CARATTERISTICHE TECNICHE TECHNICAL SPECIFICATIONS	METODI DI PROVA NORMA ISO STANDARD	VALORI PRESCRITTI DALLE NORME INTERNATIONAL STANDARDS UNI EN 14411 - ISO 13006		PRESTAZIONI PERFORMANCES
	LATI SIDES СТОРОНЫ	ISO 10545-2	± 0,6%	±2.0 mm	CONFORME COMPLIANT УСТУПЧИВЫЙ
	SPESSORE THICKNESS ТОЛЩИНА		± 5%	±0.5 mm	CONFORME COMPLIANT УСТУПЧИВЫЙ
	RETTILINEITÀ DEGLI SPIGOLI STRAIGHTNESS OF EDGES ПРЯМОЛИНЕЙНОСТЬ КРОМОК		± 0,5%	±1.5 mm	CONFORME COMPLIANT УСТУПЧИВЫЙ
	ORTOGONALITÀ RECTANGULARITY ОРТОГОНАЛЬНОСТЬ		± 0,5%	±2.0 mm	CONFORME COMPLIANT УСТУПЧИВЫЙ
	PLANARITÀ SURFACE FLATNESS ПЛОСКОСТНОСТЬ		± 0,5%	±2.0 mm	CONFORME COMPLIANT УСТУПЧИВЫЙ
	ASSORBIMENTO D'ACQUA WATER ABSORPTION ПОГЛОЩЕНИЕ ВОДЫ	ISO 10545-3	≤ 0,5%		CONFORME COMPLIANT УСТУПЧИВЫЙ
	RESISTENZA ALLA FLESSIONE BENDING STRENGTH ПРОЧНОСТЬ НА ИЗГИБ	ISO 10545-4	≥ 35N/mm²		≥ 35N/mm²
	MODULO DI ROTTURA MODULUS OF RUPTURE МОДУЛЬ РАЗРУШЕНИЯ	ISO 10545-4	> 1300N (sp. ≥ 7,5mm)		≥ 1300N
	RESISTENZA ALL'ABRASIONE SUPERFICIALE PER LE PIASTRELLE SMALTATE RESISTANCE TO SURFACE ABRASION FOR THE ENAMELED TILES СТОЙКОСТЬ К ПОВЕРХНОСТНОМУ ИСТИРАНИЮ ЭМАЛИРОВАННОЙ ПЛИТКИ	ISO 10545-7	-		DISPONIBILE SU RICHIESTA AVAILABLE ON REQUEST
	RESISTENZA AGLI SBALZI TERMICI RESISTANCE TO THERMAL SHOCKS	ISO 10545-9	METODO DISPONIBILE AVAILABLE METHOD		RESISTE RESISTANT
	RESISTENZA AL GELO FROST RESISTANCE МОРОЗОСТОЙКОСТЬ	ISO 10545-12	METODO DISPONIBILE AVAILABLE METHOD ДОСТУПНЫЙ МЕТОД		RESISTE RESISTANT СТОЙКАЯ
	RESISTENZA AI PRODOTTI CHIMICI USO DOMESTICO E ADDITIVI PER PISCINA- RESISTANCE TO HOUSEHOLD AND SWIMMING POOL CHEMICAL PRODUCTS - СТОЙКОСТЬ К ДЕЙСТВИЮ БЫТОВЫХ ХИМИЧЕСКИХ СРЕДСТВ, ДОБАВКАМ В БАССЕЙНЫ	ISO 10545-13	min. B		CONFORME COMPLIANT УСТУПЧИВЫЙ
	RESISTENZA ALLE MACCHIE STAIN RESISTANCE СТОЙКОСТЬ К ОБРАЗОВАНИ	ISO 10545-14	minimum classe 3		CONFORME COMPLIANT УСТУПЧИВЫЙ
				NATURAL	**TEXTURE**
	RESISTENZA ALLO SCIVOLAMENTO SKID RESISTANCE	DIN 51130		R10	R11
		DIN 51097		A+B	A+B
		DCOF ANSI A137.1		> 0,42 WET	> 0,42 WET
		BRITISH PENDULUM BS 7976-2		39	

I valori riflettono una media tra diversi test eseguiti secondo le normative di riferimento condotti nei nostri laboratori e/o presso centri di analisi esterni certificati. I valori di singole produzioni possono variare. / Values are based on an average of the results of various tests, which, according to required standards, have been conducted in our certified laboratories or external dedicated centers. Values of each individual production may vary.

Alcune impurità e puntinature visibili nei colori chiari sono da considerarsi una caratteristica tecnica del prodotto. Some light impurities and dots must be considered as a standard feature of the product.

Per ulteriori informazioni visita il nostro sito: www.decoratoribassanesi.it - For further information visit: www.decoratoribassanesi.it - Pour plus d'informations, visitez notre site : www.decoratoribassanesi.it - Für weitere Informationen besuchen Sie unsere Webseite: www.decoratoribassanesi.it - Для получения дополнительной информации посетите: www.decoratoribassanesi.it

DECORATORI® BASSANESI
ITALIA 1988

Caratteristiche tecniche Copenhagen

Technical specifications / caractéristiques techniques / technische eigenschaften / технические характеристики

Le nostre lastre sono sempre rettificate e hanno dimensioni finali in mm come da tabella.
Fuga minima consigliata 2 mm.

Our slabs are always rectified and the table below indicates their final size in mm.
The minimal recommended joint spacing is 2mm

Nos plaques sont toujours rectifiées et ont des dimensions finales en mm comme suivant le tableau.
Joint minimum conseillé 2 mm.

Unsere Platten sind immer geschliffen und haben endgültige Abmessungen in mm entsprechend der Tabelle. Empfohlene Mindestfuge 2 mm

Наши плиты всегда обрезаны и имеют конечные размеры, в миллиметрах, указанные в таблицах. рекомендуемый минимальный шов 2мм

Formato nominale (cm) Nominal size (cm) - Format nominal (cm) Nominales Format (cm) Номинальный форма (см)	Formato rettificato (mm) Rectified size (mm) - Format rectifié (mm) Geschliffenes Format (mm) Обрезной формат (мм)
90x90	897x897
45x90	447,5x897
22,5x90	222,75x897
22,5x45	222,75x447,5
Stick 22,5x22,5 (Listello 4,5x22,5)	Stick 222,75x222,75 (Listello 42,95x222,75)
Mosaico 31,5x31,5 (Tessera 4,5x4,5)	312,65x312,65 (Tessera 42,95x42,95)

Stucco Consigliato/ Recommended Filling / Plâtre Conseillé / Empfohlene Fugenmasse / Рекомендованная Затирка

	KERAKOLL FUGABELLA COLOR
Paper	21
Stone	08
Desert	25
Powder	07
Clay	31

Copenhagen

Design:
Norm Architects



Diciotto diverse facce, sia nella versione **NATURAL** che **TEXTURE**, si mescolano casualmente per dare vita a un pavimento sempre diverso.

Eighteen different faces, both in **NATURAL** and **TEXTURE** finishing, mixed randomly, to inspire always new floor covering.

Dix-huit faces différents, soit dans la version **NATURAL** que **TEXTURE**, se mélangent au hasard pour donner vie à un sol toujours différent.

Achtzehn verschiedene Gesichter, sowohl in der Ausführung **NATURAL**- als auch **TEXTURE**-Oberfläche, werden nach dem Zufallsprinzip gemischt um immer neue Bodenbeläge zu inspirieren.

Восемнадцать различные плиты, и в варианте **NATURAL**, и в варианте **ТЕКСТУРЫ**, смешиваются случайным образом, чтобы создать пол, который всегда новый и разный.

DECORATORI® BASSANESI ITALIA 1988